Page 1 of 1

Report Template - Rev. (3) Jul 2021 Authorised by M. A.



Boral Construction Materials Materials Technical Services

Unit 4, 3-5 Gibbon Road Baulkham Hills NSW 2153 Australia PO Box 400, Winston Hills NSW 2153

T: +61 (02) 9624 9900 F: +61 (02) 9624 9999

www.boral.com.au

TEST REPORT - MILLED SLAG

CLIENT:

BORAL CEMENT – MALDON CEMENT

FILE NO.:

50/21

ADDRESS:

Maldon Bridge Road, Maldon, NSW 2571

REQUEST NO.: 94977

LAB SAMPLE NO: 254980

SOURCE OF SAMPLE: Maldon

DATE RECEIVED: 10/06/2021

SAMPLE IDENTIFICATION: Environment ID # MDDNM2101715 - w/e 12/06/2021 - Date sampled: 07/06/2021

IDENTIFICATION OF CEMENT USED: Boral Cement SL Berrima Ref. 2019

TEST METHOD: AS 3583: Methods of test for supplementary cementitious materials for use with Portland

Cement

| PROPERTY | TEST METHOD | RESULT | DATE TESTED |
|--|-------------|--------|-------------|
| Fineness by the 45µm sieve | AS 3583.1 | 99% | 15/07/2021 |
| Relative density | AS 3583.5 | 2.93 | 16/06/2021 |
| Relative water requirement | AS 3583.6 | 99% | 17/06/2021 |
| Relative strength 7 days (accelerated) | AS 3583.6 | 100% | 24/06/2021 |
| Relative strength 28 days (standard) | AS 3583.6 | 99% | 15/07/2021 |

Parisa Sowti, Violeta Paicu, Brad Vanderburg, Mat File, File

Note:

Sample was provided by the client and tested as received.



Olicia Julius Alvaro Approved Signator CEM94977.JA.1 Date 15/07 Serial No.

Build something great™

Page 1 of 1

Report Template - Rev. (3) July 2021 - Authorised by M.A.



Boral Construction Materials Materials Technical Services

Unit 4, 3-5 Gibbon Road Baulkham Hills NSW 2153 Australia PO Box 400, Winston Hills NSW 2153

T: +61 (02) 9624 9900 F: +61 (02) 9624 9999

www.boral.com.au

TEST REPORT

CLIENT:

BORAL CEMENT - Maldon Cement

Maldon Bridge Road, Maldon, NSW 2571,

PROJECT:

Testing of Maldon Environment Weekly Sample.

FILE No.:50/21

REQUEST No.: 94977

TEST PROCEDURE:

AS 3583.12 - 1991 - Determination of Available Alkali

Laboratory Sample No.:

254980

Date Sampled:

07/06/21

Date Received:

10/06/21

Date Tested:

11/08/21

Sample Description:

Enviroment ID#

MDDNM2101715

Field No.:

1

TEST RESULTS:

Sodium as Na₂O (%)

0.04

Potassium as K₂O (%)

0.07

Available Alkali (%)

0.1

Available Alkali (%) = Na_2O (%) + (0.658 x K_2O %)

Note:

Sample was provided by the Client and tested as received.

V.Paicu, B.Vanderburg, P.Sowti, Mat.File, File.

NATA

ACCREDITED FOR
TECHNICAL
COMPETENCE

Approved Signatory_

Nanthini Selvadurai

Date 16-08-21

_ Serial No.

CHFM94977 NS 1__



Boral Construction Materials Materials Technical Services

Unit 4, 3-5 Gibbon Road Baulkham Hills NSW 2153 Australia PO Box 400, Winston Hills NSW 2153

T: +61 (02) 9624 9900 F: +61 (02) 9624 9999

www.boral.com.au

TEST REPORT

CLIENT:

BORAL CEMENT - MALDON CEMENT

Maldon Bridge Road, Maldon, NSW 2571.

PROJECT:

Testing of Maldon Environment Weekly Sample.

FILE No.:50 / 21

REQUEST No.: 94977

TEST PROCEDURE: AS 3583.7 – Determination of Sulfide Sulfur content

Laboratory Sample No.:

254980

Date Sampled:

07/06/2021

Date Received:

10/06/2021

Date Tested:

17/08/2021

Sample Description:

Enviroment ID

MDDNM2101715

Field No.:

1

TEST RESULTS:

Sulfide Sulfur as S (%)

0.40

Sample submitted by the Client.

- Sample was provided by the Client.
- Test results in this test report relate only to the sample tested.
- This report shall not be reproduced except in full without the approval of the Boral MTS Laboratory.

Taylah Cali

17th August 2021

Violeta Paicu, Brad Vanderburg, Parisa Sowt, Mat.File, File.