



**Boral Construction Materials  
Materials Technical Services**

Unit 4, 3-5 Gibbon Road  
Baulkham Hills NSW 2153 Australia  
PO Box 400, Winston Hills NSW 2153

T: +61 (02) 9624 9900

F: +61 (02) 9624 9999

www.boral.com.au

**TEST REPORT – MILLED SLAG**

**CLIENT:** BORAL CEMENT – MALDON CEMENT

**FILE NO.:** 50/21

**ADDRESS:** Maldon Bridge Road, Maldon, NSW 2571

**REQUEST NO.:** 96082

**LAB SAMPLE NO:** 257646

**SOURCE OF SAMPLE:** Maldon

**DATE RECEIVED:** 02/09/2021

**SAMPLE IDENTIFICATION:** Enviroment ID # MDDNM2102658 - w/e 04/09/2021 - Date sampled: 30/08/2021

**IDENTIFICATION OF CEMENT USED:** Boral Cement SL Berrima Ref. 2019

**TEST METHOD: AS 3583:** Methods of test for supplementary cementitious materials for use with Portland Cement

PROPERTY	TEST METHOD	RESULT	DATE TESTED
Fineness by the 45µm sieve	AS 3583.1	99%	07/10/2021
Relative density	AS 3583.5	2.91	08/09/2021
Relative water requirement	AS 3583.6	100%	09/09/2021
Relative strength 7 days (accelerated)	AS 3583.6	110%	16/09/2021
Relative strength 28 days (standard)	AS 3583.6	106%	07/10/2021

Parisa Sowti, Violeta Paicu, Brad Vanderburg, Mat File, File

**Note:**

- Sample was provided by the client and tested as received.



Approved Signatory Julius Alvaro Serial No. CEM96082.JA.1  
Date 08/10/2021

Accredited for compliance with ISO/IEC 17025 - Testing  
This report shall not be reproduced except in full without the approval of the Boral MTS Laboratory  
Test results in this Test Report relate only to the samples tested

NATA Accredited Laboratory

Number: 547



**Boral Construction Materials  
Materials Technical Services**

Unit 4, 3-5 Gibbon Road  
Baulkham Hills NSW 2153 Australia  
PO Box 400, Winston Hills NSW 2153

T: +61 (02) 9624 9900

F: +61 (02) 9624 9999

www.boral.com.au

**TEST REPORT**

CLIENT: BORAL CEMENT – Maldon Cement  
Maldon Bridge Road, Maldon, NSW 2571.

FILE No.:50/21

PROJECT: Testing of Maldon Environment Weekly Sample.

REQUEST No.: 96082

**TEST PROCEDURE:**

AS 3583.12 – 1991 – Determination of Available Alkali

Laboratory Sample No.: 257646  
Date Sampled: 30/08/21  
Date Received: 02/09/21  
Date Tested: 07/10/21  
Sample Description: Environment ID #  
MDDNM2102658  
Field No.: 1

**TEST RESULTS:**

Sodium as Na<sub>2</sub>O (%) 0.05  
Potassium as K<sub>2</sub>O (%) 0.07  
Available Alkali (%) 0.1

Available Alkali (%) = Na<sub>2</sub>O (%) + (0.658 x K<sub>2</sub>O %)

**Note:**

- Sample was provided by the Client and tested as received.

V.Paicu, B.Vanderburg,P.Sowti, Mat.File, File.



Approved Signatory

Nanthini Selvadurai

Date 07-10-21

Serial No. CHEM96082.NS.1

NATA Accredited Laboratory

Accredited for compliance with ISO/IEC 17025 - Testing  
This report shall not be reproduced except in full without the approval of the Boral MTS Laboratory  
Test results in this Test Report relate only to the samples tested

Number: 9968