

Page 1 of 1
Report Template - Rev. (3) Jul 2021 Authorised by M. A.

# **Boral Construction Materials Materials Technical Services**

Unit 4, 3–5 Gibbon Road Baulkham Hills NSW 2153 Australia

PO Box 400, Winston Hills NSW 2153

T +61 (02) 9624 9900

#### TEST REPORT - MILLED SLAG

boral.com.au

CLIENT:

BORAL CEMENT - MALDON CEMENT

**FILE NO: 50/22** 

ADDRESS:

Maldon Bridge Road, Maldon, NSW 2571

**REQUEST NO: 98732** 

**LAB SAMPLE NO: 265096** 

**SOURCE OF SAMPLE: Maldon** 

**DATE RECEIVED: 24/03/2022** 

SAMPLE IDENTIFICATION: Environment ID # MDDNM2200740 - w/e 26/03/2022 - Date sampled: 21/03/2022

IDENTIFICATION OF CEMENT USED: Boral Cement SL Berrima Ref. 2019

TEST METHOD: AS 3583: Methods of test for supplementary cementitious materials for use with Portland

Cement

TEST METHOD	RESULT	DATE TESTED
AS 3583.1	99%	28/04/2022
AS 3583.5	2.91	29/03/2022
AS 3583.6	100%	31/03/2022
AS 3583.6	110%	07/04/2022
AS 3583.6	106%	28/04/2022
	AS 3583.1 AS 3583.5 AS 3583.6 AS 3583.6	AS 3583.1 99% AS 3583.5 2.91 AS 3583.6 100% AS 3583.6 110%

Parisa Sowti, Violeta Paicu, Brad Vanderburg, Mat File, File

Note:

Sample was provided by the client and tested as received.

Approved Signator Cluary Julius Alvaro

Date 03/05/2022 Serial No. CEM98732.JA.1





Page 1 of 1

Report Template - Rev. (3) July 2021 - Authorised by M.A.



## **Boral Construction Materials Materials Technical Services**

Unit 4, 3-5 Gibbon Road Baulkham Hills NSW 2153 Australia PO Box 400, Winston Hills NSW 2153

T: +61 (02) 9624 9900 F: +61 (02) 9624 9999

www.boral.com.au

**TEST REPORT** 

CLIENT: BORAL CEM

BORAL CEMENT – Maldon Cement

Maldon Bridge Road, Maldon, NSW 2571.

PROJECT:

Testing of Maldon Environment Weekly Sample.

FILE No.:50/22

REQUEST No.: 98732

### **TEST PROCEDURE:**

AS 3583.12 - 1991 - Determination of Available Alkali

Laboratory Sample No.:

265096

Date Sampled:

21/03/2022

Date Received:

26/03/2022

Date Tested:

02/05/2022

Sample Description:

Environment ID#

MDDNM2200740

Field No.:

1

### **TEST RESULTS:**

Sodium as Na<sub>2</sub>O (%)

0.05

Potassium as K<sub>2</sub>O (%)

0.07

Available Alkali (%)

0.1

Available Alkali (%) =  $Na_2O$  (%) + (0.658 x  $K_2O$  %)

#### Note:

Sample was provided by the Client and tested as received.

V.Paicu, B.Vanderburg, P.Sowti, Mat.File, File.

NATA

ACCREDITED FOR
TECHNICAL
COMPETENCE

Approved Signatory\_

Date \_O2

1111

Nanthini Selvadurai

 o 5 ~ 22
 Serial No. \_\_\_\_

CHEM98732.NS.1

Accredited for compliance with ISO/IEC 17025 - Testing
This report shall not be reproduced except in full without the approval of the Boral MTS Laboratory
Test results in this Test Report relate only to the samples tested

NATA Accredited Laboratory

Number: 9968