

## FINAL REPORT

CERTIFICATE No.: 24823



Boral Cement Limited  
N 62 008 528 523  
Taylor Avenue New Berrima NSW 2577  
Locked Bag 4 New Berrima NSW 2577  
T +61 2 4860 2222

TEST CERTIFICATE OF: Maldon Daily Despatch Environment  
PRODUCED AT: Boral Cement Limited Maldon  
TESTED AT: Berrima Works Laboratory  
SAMPLE IDENTIFICATION: MDDNM2301480  
DATE DESPATCHED: 1/05/2023

PROPERTY	REQUIREMENTS OF AS 3582.2	RESULT
Insoluble Residue (AS 3583.14)		0.6 %
LOI (AS 3583.3)		-0.8 %
SO <sub>3</sub> (AS 2350.2; TM 10.01.07)		0.4 %
MgO (AS 2350.2)	≤ 15.0 %	5.9 %
Al <sub>2</sub> O <sub>3</sub> (AS 2350.2)	≤ 18.0 %	13.8 %
Fe <sub>2</sub> O <sub>3</sub> (AS 2350.2)		1.1 %
expressed as FeO *		1.0 %
Mn <sub>2</sub> O <sub>3</sub> (AS 2350.2)		0.4 %
expressed as MnO *		0.4 %
Total Alkali (AS 2350.2)		0.4 %
Cl (AS 2350.2)	≤ 0.1 %	< 0.01 %
45µm Residue (AS 3583.1)		1.3 %
Fineness Index (AS 2350.8)		425 m <sup>2</sup> /kg

### REMARKS

Sampling not carried out by laboratory. Samples tested as received.

\* NATA accreditation does not cover the performance of this service.



Accredited for compliance with ISO/IEC 17025 - Testing



---

Marc Smith  
Technical Services Manager

**TEST REPORT – MILLED SLAG****CLIENT:** BORAL CEMENT – MALDON CEMENT**FILE NO:** 50/23**ADDRESS:** Maldon Bridge Road, Maldon, NSW 2571**REQUEST NO:** 105542**LAB SAMPLE NO:** 283135**SOURCE OF SAMPLE:** Maldon**DATE RECEIVED:** 04/05/2023**SAMPLE IDENTIFICATION:** Enviroment ID # MDDNM2301480- w/e 06/05/2023 - Date sampled: 01/05/2023**IDENTIFICATION OF CEMENT USED:** Boral Cement SL Berrima Ref. 2022**TEST METHOD: AS 3583:** Methods of test for supplementary cementitious materials for use with Portland cement

PROPERTY	TEST METHOD	RESULT	DATE TESTED
Relative density	AS 3583.5	2.94	08/05/2023
Relative water requirement	AS 3583.6	99%	11/05/2023
Relative strength 7 days (accelerated)	AS 3583.6	112%	18/05/2023
Relative strength 28 days (standard)	AS 3583.6	110%	08/06/2023

Parisa Sowti, Violeta Paicu, Brad Vanderburg, Stephanie Koehler, Mat File, File

**Note:**

- Sample supplied by the client and tested as received.

Approved Signatory



Julius Alvaro

Date

13/06/2023

Serial No.

CEM105542.JA.1

Accredited for compliance with ISO/IEC 17025 – Testing  
This report shall not be reproduced in full without the approval of the Boral MTS Laboratory.  
Test results in this Test Report relate only to the samples tested.

**NATA Accredited Laboratory  
Number: 547**



**Boral Construction Materials  
Materials Technical Services**

Unit 4, 3-5 Gibbon Road  
Baulkham Hills NSW 2153 Australia  
PO Box 400, Winston Hills NSW 2153

T: +61 (02) 9624 9900

F: +61 (02) 9624 9999

www.boral.com.au

**TEST REPORT**

CLIENT: BORAL CEMENT – MALDON CEMENT  
Maldon Bridge Road, Maldon, NSW 2571.

FILE No.:50 / 23

PROJECT: Testing of Maldon Environment weekly sample.

REQUEST No.: 105542

**TEST PROCEDURE:** AS 3583.7 – Determination of Sulfide Sulfur content

Laboratory Sample No.: 283135  
Date Sampled: 01/05/2023  
Date Received: 04/05/2023  
Date Tested: 26/05/2023  
Sample Description: Environment  
ID # MDDNM2301480  
Field No.: 1

**TEST RESULTS:**

Sulfide Sulfur as S (%) 0.24

Sample submitted by the Client.

- Sample was provided by the Client.
- Test results in this test report relate only to the sample tested.
- This report shall not be reproduced except in full without the approval of the Boral MTS Laboratory.

Nanthini S

29<sup>th</sup> May 2023

Parisa Sowti, Violeta Paicu, Brad Vanderburg, Stephanie, Koehler, Mat.File, File.