

FINAL REPORT

CERTIFICATE No.: 25441



Boral Cement Limited

N 62 008 528 523

Taylor Avenue New Berrima NSW 2577

Locked Bag 4 New Berrima NSW 2577

T +61 2 4860 2222

TEST CERTIFICATE OF: Maldon Daily Despatch Environment
PRODUCED AT: Boral Cement Limited Maldon
TESTED AT: Berrima Works Laboratory
SAMPLE IDENTIFICATION: MDDNM2304531
DATE DESPATCHED: 1/11/2023

PROPERTY	REQUIREMENTS OF AS 3582.2	RESULT
Insoluble Residue (AS 3583.14)		0.4 %
LOI (AS 3583.3)		-0.7 %
SO ₃ (AS 2350.2; TM 10.01.07)		0.3 %
MgO (AS 2350.2)	≤ 15.0 %	5.8 %
Al ₂ O ₃ (AS 2350.2)	≤ 18.0 %	13.4 %
Fe ₂ O ₃ (AS 2350.2)		0.9 %
expressed as FeO *		0.8 %
Mn ₂ O ₃ (AS 2350.2)		0.4 %
expressed as MnO *		0.4 %
Total Alkali (AS 2350.2)		0.4 %
Cl (AS 2350.2)	≤ 0.1 %	< 0.01 %
Fineness passing 45µm sieve (AS 3583.1)		99 %
Fineness Index (AS 2350.8)		420 m ² /kg

REMARKS

Sampling not carried out by laboratory. Samples tested as received.

* NATA accreditation does not cover the performance of this service.



Accredited for compliance with ISO/IEC 17025 - Testing

Marc Smith
Technical Services Manager

**Boral Construction Materials
Materials Technical Services**Unit 4, 3-5 Gibbon Road
Baulkham Hills NSW 2153 Australia

PO Box 400, Winston Hills NSW 2153

T +61 (02) 9624 9900

boral.com.au**TEST REPORT – MILLED SLAG****CLIENT:** BORAL CEMENT – MALDON CEMENT**FILE NO:** 50/23**ADDRESS:** Maldon Bridge Road, Maldon, NSW 2571**REQUEST NO:** 108799**LAB SAMPLE NO:** 293285**SOURCE OF SAMPLE:** Maldon**DATE RECEIVED:** 02/11/2023**SAMPLE IDENTIFICATION:** Enviroment ID # MDDNM2304531- w/e 04/11/2023 - Date sampled: 01/11/2023**IDENTIFICATION OF CEMENT USED:** Boral Cement SL Berrima Ref. 2022**TEST METHOD: AS 3583:** Methods of test for supplementary cementitious materials for use with Portland cement

PROPERTY	TEST METHOD	RESULT	DATE TESTED
Relative density	AS 3583.5	2.94	08/11/2023
Relative water requirement	AS 3583.6	99%	09/11/2023
Relative strength 7 days (accelerated)	AS 3583.6	116%	16/11/2023
Relative strength 28 days (standard)	AS 3583.6	114%	07/12/2023

Parisa Sowti, Violeta Paicu, Brad Vanderburg, Mat File, File

Note:

- Sample supplied by the client and tested as received.

Approved Signatory



Sam El-Hamawi

Date

11/12/23

Serial No.

CEM108799.SE.1



Accredited for compliance with ISO/IEC 17025 – Testing

This report shall not be reproduced in full without the approval of the Boral MTS Laboratory.
Test results in this Test Report relate only to the samples tested.**NATA Accredited Laboratory**
Number: 547



**Building
something
great**

TEST REPORT

CLIENT: BORAL CEMENT – MALDON CEMENT
Maldon Bridge Road, Maldon, NSW 2571.

FILE No.:50 / 23

PROJECT: Testing of Maldon Enviroment weekly sample.

REQUEST No.: 108799

TEST PROCEDURE: AS 3583.7 – Determination of Sulfide Sulfur content

Laboratory Sample No.: 293285
Date Sampled: 01/11/2023
Date Received: 02/11/2023
Date Tested: 24/11/2023
Sample Description: Enviroment
ID # MDDNM2304531
Field No.: 1

TEST RESULTS:

Sulfide Sulfur as S (%) 0.16

Sample submitted by the Client.

- Sample was provided by the Client.
- Test results in this test report relate only to the sample tested.
- This report shall not be reproduced except in full without the approval of the Boral MTS Laboratory.

Nanthini S

27th November 2023

Parisa Sowti, Violeta Paicu, Brad Vanderburg, Mat.File, File.