

FINAL REPORT

CERTIFICATE No.: 25615



Boral Cement Limited

N 62 008 528 523

Taylor Avenue New Berrima NSW 2577

Locked Bag 4 New Berrima NSW 2577

T +61 2 4860 2222

TEST CERTIFICATE OF: Maldon Daily Despatch Environment
PRODUCED AT: Boral Cement Limited Maldon
TESTED AT: Berrima Works Laboratory
SAMPLE IDENTIFICATION: MDDNM2400058
DATE DESPATCHED: 3/01/2024

PROPERTY	REQUIREMENTS OF AS 3582.2	RESULT
Insoluble Residue (AS 3583.14)		0.5 %
LOI (AS 3583.3)		-1.0 %
SO ₃ (AS 2350.2; TM 10.01.07)		-0.7 %
MgO (AS 2350.2)	≤ 15.0 %	5.6 %
Al ₂ O ₃ (AS 2350.2)	≤ 18.0 %	13.0 %
Fe ₂ O ₃ (AS 2350.2)		0.8 %
expressed as FeO *		0.7 %
Mn ₂ O ₃ (AS 2350.2)		0.4 %
expressed as MnO *		0.4 %
Total Alkali (AS 2350.2)		0.5 %
Cl (AS 2350.2)	≤ 0.1 %	< 0.01 %
Fineness passing 45µm sieve (AS 3583.1)		99 %
Fineness Index (AS 2350.8)		415 m ² /kg

REMARKS

Sampling not carried out by laboratory. Samples tested as received.

* NATA accreditation does not cover the performance of this service.



Accredited for compliance with ISO/IEC 17025 - Testing



Marc Smith
Technical Services Manager



**Building
something
great**

Unit 4, 3-5 Gibbon Road,
Baulkham Hills NSW 2153 Australia
PO Box 400,
Winston Hills NSW 2153

T +61 (02) 9624 9900
boral.com.au

TEST REPORT – MILLED SLAG

CLIENT: BORAL CEMENT – MALDON CEMENT

FILE NO: 50/24

ADDRESS: Maldon Bridge Road, Maldon, NSW 2571

REQUEST NO: 109942

LAB SAMPLE NO: 296757

SOURCE OF SAMPLE: Maldon

DATE RECEIVED: 11/01/2024

SAMPLE IDENTIFICATION: Enviroment ID # MDDNM2400058- w/e 06/01/2024 - Date sampled: 03/01/2024

IDENTIFICATION OF CEMENT USED: Boral Cement SL Berrima Ref. 2022

TEST METHOD: AS 3583: Methods of test for supplementary cementitious materials for use with Portland cement

PROPERTY	TEST METHOD	RESULT	DATE TESTED
Relative density	AS 3583.5	2.93	11/01/2024
Relative water requirement	AS 3583.6	99%	11/01/2024
Relative strength 7 days (accelerated)	AS 3583.6	118%	18/01/2024
Relative strength 28 days (standard)	AS 3583.6	114%	08/02/2024

Parisa Sowti, Violeta Paicu, Brad Vanderburg, Mat File, File

Note:

- Sample supplied by the client and tested as received.

Approved signatory

Sam El-Hamawi

Date

19/02/2024

Serial no.

CEM109942.SE.1





**Building
something
great**

Unit 4, 3-5 Gibbon Road,
Baulkham Hills NSW 2153 Australia
PO Box 400,
Winston Hills NSW 2153

T +61 (02) 9624 9900
boral.com.au

TEST REPORT

CLIENT: BORAL CEMENT – MALDON CEMENT
Maldon Bridge Road, Maldon, NSW 2571.

FILE No.:50 / 24

PROJECT: Testing of Maldon Enviroment Sample.

REQUEST No.: 109942

TEST PROCEDURE: AS 3583.7 – Determination of Sulfide Sulfur content

Laboratory Sample No.: 296757
Date Sampled: 03/01/2024
Date Received: 11/01/2024
Date Tested: 31/01/2024
Sample Description: Enviroment
ID # MDDNM2400058
Field No.: 1

TEST RESULTS:

Sulfide Sulfur as S (%) 0.04

Sample submitted by the Client.

- Sample was provided by the Client.
- Test results in this test report relate only to the sample tested.
- This report shall not be reproduced except in full without the approval of the Boral MTS Laboratory.

Nanthini S

02nd February 2024.

Parisa Sowti, Violeta Paicu, Brad Vanderburg, Mat.File, File.