## **FINAL REPORT**

CERTIFICATE No.: 23095



Boral Cement Limited ABN 62 008 528 523 Taylor Avenue New Berrima NSW 2577 Locked Bag 4 New Berrima NSW 2577 T +61 2 4860 2222 F +61 2 4860 2257

| TEST CERTIFICATE OF:   | Maldon Daily Despatch Off White Cement |  |  |
|------------------------|--|--|--|
| PRODUCED AT:           | Boral Cement Limited Maldon            |  |  |
| TESTED AT:             | Berrima Works Laboratory               |  |  |
| SAMPLE IDENTIFICATION: | MDDOW2103665                           |  |  |
| DATE DESPATCHED:       | 29/11/2021                             |  |  |

| PROPERTY                          | REQUIREM | ENTS OF AS 3972 | RESULT   |
|-----------------------------------|----------|-----------------|----------|
| Compressive Strength (AS 2350.11) |          |                 |          |
| 3 Day                             |          |                 | 41.5 MPa |
| 7 Day                             | Minimum  | 35 MPa          | 53.8 MPa |
| 28 Day                            | Minimum  | 45 MPa          | 67.1 MPa |
| Setting Time (AS 2350.4)          |          |                 |          |
| Initial                           | Minimum  | 45 mins         | 120 mins |
| Final                             | Maximum  | 360 mins        | 165 mins |
| Soundness (AS 2350.5)             | Maximum  | 5 mm            | 1 mm     |
| SO <sub>3</sub> (AS 2350.2)       | Maximum  | 3.5 %           | 3.1 %    |
| CI (AS 2350.2)                    | Maximum  | 0.10 %          | 0.01 %   |

| OTHER REPORTABLE PROPERTIES |             |        |                    |               |                        |  |  |
|-----------------------------|-------------|--------|--------------------|---------------|------------------------|--|--|
| CHEM                        | ICAL        |        | PHYSICAL           |               |                        |  |  |
| K <sub>2</sub> O            | (AS 2350.2) | 0.42 % | Normal Consistency | (AS 2350.3)   | 28.5 %                 |  |  |
| Na <sub>2</sub> O           | (AS 2350.2) | 0.08 % | Fineness Index     | (AS 2350.8)   | 395 m <sup>2</sup> /kg |  |  |
| LOI                         | (AS 2350.2) | 1.7 %  | Brightness *       | (TM 10.01.12) | 70.2 %                 |  |  |
|                             |             |        |                    |               |                        |  |  |

## REMARKS

Preparation of mortar and moulding of specimens in accordance with AS 2350.12.

Sampling not carried out by laboratory. Samples tested as received.

This cement is a Type GP cement with up to 7.5% mineral addition.

\* NATA accreditation does not cover the performance of this service.

