

FINAL REPORT

CERTIFICATE No.: 23581



Boral Cement Limited
N 62 008 528 523
Taylor Avenue New Berrima NSW 2577
Locked Bag 4 New Berrima NSW 2577
T +61 2 4860 2222

TEST CERTIFICATE OF: Maldon Daily Despatch Off White Cement
PRODUCED AT: Boral Cement Limited Maldon
TESTED AT: Berrima Works Laboratory
SAMPLE IDENTIFICATION: MDDOW2201190
DATE DESPATCHED: 26/04/2022

PROPERTY	REQUIREMENTS OF AS 3972		RESULT
SO ₃ (AS 2350.2)	Maximum	3.5 %	2.8 %
Cl (AS 2350.2)	Maximum	0.10 %	0.02 %

OTHER REPORTABLE PROPERTIES

CHEMICAL

K₂O (AS 2350.2) 0.41 %
Na₂O (AS 2350.2) 0.06 %
LOI (AS 2350.2) 3.1 %

PHYSICAL

Fineness Index (AS 2350.8) 400 m²/kg
Brightness * (TM 10.01.12) 72.3 %

REMARKS

Sampling not carried out by laboratory. Samples tested as received.

This cement is a Type GP cement with up to 7.5% mineral addition.

* NATA accreditation does not cover the performance of this service.



Accredited for compliance with ISO/IEC 17025 - Testing

NATA Accreditation Number: 530 / 531

Page 1 of 1

Marc Smith
Technical Services Manager
Date of Issue: 26/07/2022

**Boral Construction Materials
Materials Technical Services**Unit 4, 3-5 Gibbon Road
Baulkham Hills NSW 2153 Australia

PO Box 400, Winston Hills NSW 2153

T +61 (02) 9624 9900

boral.com.au**TEST REPORT****CLIENT:** BORAL CEMENT – (TECHNICAL)**FILE NO:** 50/22**ADDRESS:** 39 Delhi Road, North Ryde, NSW 2113**REQUEST NO:** 99442**TEST METHOD:** AS/NZS 2350: Method of Testing Portland and Blended Cements**CEMENT IDENTIFICATION:** MDDOW2201190**LAB. SAMPLE NO:** 267105**SAMPLE SOURCE:** Maldon**DATE SAMPLED:** 26/04/2022**DATE RECEIVED:** 10/05/2022**Results**Date of cast: 20/05/2022

PROPERTY	DATE TESTED	TEST METHOD	RESULT
Compressive strength - 1 day	21/05/2022	AS/NZS 2350.11	24.9 MPa
Compressive strength - 3 days	23/05/2022	AS/NZS 2350.11	44.3 MPa
Compressive strength - 7 days	27/05/2022	AS/NZS 2350.11	53.1 MPa
Compressive strength - 28 days	17/06/2022	AS/NZS 2350.11	61.1 MPa
Normal Consistency	27/06/2022	AS/NZS 2350.3	28.8%
Setting Time Initial Set	27/06/2022	AS/NZS 2350.4	120 Minutes
Final Set	27/06/2022	AS/NZS 2350.4	195 Minutes
Soundness	28/06/2022	AS/NZS 2350.5	1 mm

Note:

- Cement was provided by the client and tested as received.

Marc Smith, Parisa Sowti, Violeta Paicu, Mat. File, File

Approved Signatory



Julius Alvaro

Date

04/07/2022

Serial No.

CEM99442.JA.5

Accredited for compliance with ISO/IEC 17025 – Testing

This report shall not be reproduced in full without the approval of the Boral MTS Laboratory.

Test results in this Test Report relate only to the samples tested.

**NATA Accredited Laboratory**
Number: 547