

FINAL REPORT

CERTIFICATE No.: 23623



Boral Cement Limited
N 62 008 528 523
Taylor Avenue New Berrima NSW 2577
Locked Bag 4 New Berrima NSW 2577
T +61 2 4860 2222

TEST CERTIFICATE OF: Maldon Daily Despatch Off White Cement
PRODUCED AT: Boral Cement Limited Maldon
TESTED AT: Berrima Works Laboratory
SAMPLE IDENTIFICATION: MDDOW2201383
DATE DESPATCHED: 9/05/2022

PROPERTY	REQUIREMENTS OF AS 3972		RESULT
SO ₃ (AS 2350.2)	Maximum	3.5 %	2.9 %
Cl (AS 2350.2)	Maximum	0.10 %	0.01 %

OTHER REPORTABLE PROPERTIES

CHEMICAL

K₂O (AS 2350.2) 0.41 %
Na₂O (AS 2350.2) 0.08 %
LOI (AS 2350.2) 1.5 %

PHYSICAL

Fineness Index (AS 2350.8) 395 m²/kg
Brightness * (TM 10.01.12) 70.3 %

REMARKS

Sampling not carried out by laboratory. Samples tested as received.

This cement is a Type GP cement with up to 7.5% mineral addition.

* NATA accreditation does not cover the performance of this service.



Accredited for compliance with ISO/IEC 17025 - Testing

NATA Accreditation Number: 530 / 531

Page 1 of 1

Marc Smith
Technical Services Manager
Date of Issue: 26/07/2022

**Boral Construction Materials
Materials Technical Services**Unit 4, 3-5 Gibbon Road
Baulkham Hills NSW 2153 Australia

PO Box 400, Winston Hills NSW 2153

T +61 (02) 9624 9900

boral.com.au**TEST REPORT****CLIENT:** BORAL CEMENT – (TECHNICAL)**FILE NO:** 50/22**ADDRESS:** 39 Delhi Road, North Ryde, NSW 2113**REQUEST NO:** 99584**TEST METHOD:** AS/NZS 2350: Method of Testing Portland and Blended Cements**CEMENT IDENTIFICATION:** MDDOW2201383**LAB. SAMPLE NO:** 267447**SAMPLE SOURCE:** Maldon**DATE SAMPLED:** 09/05/2022**DATE RECEIVED:** 17/05/2022**Results**Date of cast: 20/06/2022

PROPERTY	DATE TESTED	TEST METHOD	RESULT
Compressive strength - 1 day	21/06/2022	AS/NZS 2350.11	25.2 MPa
Compressive strength - 3 days	23/06/2022	AS/NZS 2350.11	42.0 MPa
Compressive strength - 7 days	27/06/2022	AS/NZS 2350.11	49.0 MPa
Compressive strength - 28 days	18/07/2022	AS/NZS 2350.11	59.3 MPa
Normal Consistency	22/07/2022	AS/NZS 2350.3	28.7%
Setting Time Initial Set	22/07/2022	AS/NZS 2350.4	120 Minutes
Final Set	22/07/2022	AS/NZS 2350.4	150 Minutes
Soundness	23/07/2022	AS/NZS 2350.5	1 mm

Note:

- Cement was provided by the client and tested as received.

Marc Smith, Parisa Sowti, Violeta Paicu, Mat. File, File

Approved Signatory Julius C Alvaro Julius Alvaro
Date 27/07/2022 Serial No. CEM99584.JA.7

Accredited for compliance with ISO/IEC 17025 – Testing
This report shall not be reproduced in full without the approval of the Boral MTS Laboratory.
Test results in this Test Report relate only to the samples tested.



NATA Accredited Laboratory
Number: 547