## **FINAL REPORT**

CERTIFICATE No.: 24050



Boral Cement Limited N 62 008 528 523 Taylor Avenue New Berrima NSW 2577 Locked Bag 4 New Berrima NSW 2577 T +61 2 4860 2222

TEST CERTIFICATE OF: Maldon Daily Despatch Off White Cement

PRODUCED AT: Boral Cement Limited Maldon

**TESTED AT:** Berrima Works Laboratory

SAMPLE IDENTIFICATION: MDDOW2202744

DATE DESPATCHED: 15/08/2022

PROPERTY	REQUIREMI	ENTS OF AS 3972	RESULT
Compressive Strength (AS 2350.11)			
3 Day			45.7 MPa
7 Day	Minimum	35 MPa	54.7 MPa
28 Day	Minimum	45 MPa	66.7 MPa
Setting Time (AS 2350.4)			
Initial	Minimum	45 mins	135 mins
Final	Maximum	360 mins	180 mins
Soundness (AS 2350.5)	Maximum	5 mm	1 mm
SO <sub>3</sub> (AS 2350.2)	Maximum	3.5 %	2.7 %
CI (AS 2350.2)	Maximum	0.10 %	0.01 %

CHEM	IICAL		PHYSICAL		
$K_2O$	(AS 2350.2)	0.38 %	Normal Consistency	(AS 2350.3)	28.0 %
Na <sub>2</sub> O	(AS 2350.2)	0.06 %	Fineness Index	(AS 2350.8)	$400 \text{ m}^2/\text{kg}$
LOI	(AS 2350.2)	3.9 %	Brightness *	(TM 10.01.12)	71.3 %

## **REMARKS**

Preparation of mortar and moulding of specimens in accordance with AS 2350.12.

Sampling not carried out by laboratory. Samples tested as received.

This cement is a Type GP cement with up to 7.5% mineral addition.

\* NATA accreditation does not cover the performance of this service.

Jul.

Marc Smith
Technical Services Manager
Date of Issue: 17/10/2022