FINAL REPORT

CERTIFICATE No.: 24247



Boral Cement Limited N 62 008 528 523 Taylor Avenue New Berrima NSW 2577 Locked Bag 4 New Berrima NSW 2577 T +61 2 4860 2222

TEST CERTIFICATE OF: Maldon Daily Despatch Off White Cement

PRODUCED AT: Boral Cement Limited Maldon
TESTED AT: Berrima Works Laboratory

SAMPLE IDENTIFICATION: MDDOW2203839

DATE DESPATCHED: 31/10/2022

PROPERTY		REQUIREMI	ENTS OF AS 3972		RESULT
Compressive Strength (AS 2350.11)				
3 Day	•				40.8 MPa
7 Day		Minimum	35 MPa		53.1 MPa
28 Day		Minimum	45 MPa		64.5 MPa
Setting Time (AS 2350.	4)				
Initial	•	Minimum	45 mins		120 mins
Final		Maximum	360 mins		195 mins
Soundness (AS 2350.5)		Maximum	5 mm		1 mm
SO ₃ (AS 2350.2)		Maximum	3.5 %		2.7 %
CI (AS 2350.2)		Maximum	0.10 %		0.01 %
OTHER REPORTABLE	PROPERTIES				
CHEMICAL			PHYSICAL		
K ₂ O (AS 2350.2)	0.33 %		Normal Con	sistency (AS 2350.3)	27.8 %
Na ₂ O (AS 2350.2)	0.05 %		Fineness In	dex (AS 2350.8)	395 m ² /kg
LOI (AS 2350.2)	4.1 %		Brightness *	(TM 10.01.12)	70.8 %

REMARKS

Preparation of mortar and moulding of specimens in accordance with AS 2350.12.

Sampling not carried out by laboratory. Samples tested as received.

This cement is a Type GP cement with up to 7.5% mineral addition.

* NATA accreditation does not cover the performance of this service.

Jul.

Marc Smith
Technical Services Manager
Date of Issue: 13/12/2022