FINAL REPORT

CERTIFICATE No.: 24301



Boral Cement Limited N 62 008 528 523 Taylor Avenue New Berrima NSW 2577 Locked Bag 4 New Berrima NSW 2577 T +61 2 4860 2222

TEST CERTIFICATE OF: Maldon Daily Despatch Off White Cement

PRODUCED AT: Boral Cement Limited Maldon
TESTED AT: Berrima Works Laboratory

SAMPLE IDENTIFICATION: MDDOW2204047

DATE DESPATCHED: 14/11/2022

PROPERTY		REQUIREMI	ENTS OF AS 3972		RESULT
Compressive Strength (AS 2350.11)				
3 Day	,				38.7 MPa
7 Day		Minimum	35 MPa		51.0 MPa
28 Day		Minimum	45 MPa		65.2 MPa
Setting Time (AS 2350.	.4)				
Initial		Minimum	45 mins		150 mins
Final		Maximum	360 mins		210 mins
Soundness (AS 2350.5)		Maximum	5 mm		1 mm
SO ₃ (AS 2350.2)		Maximum	3.5 %		2.8 %
CI (AS 2350.2)		Maximum	0.10 %		0.01 %
OTHER REPORTABLE	PROPERTIES				
CHEMICAL			PHYSICAL		
K ₂ O (AS 2350.2)	0.44 %		Normal Consister	ncy (AS 2350.3)	27.8 %
Na ₂ O (AS 2350.2)	0.06 %		Fineness Index	(AS 2350.8)	410 m ² /kg
LOI (AS 2350.2)	3.9 %		Brightness *	(TM 10.01.12)	71.0 %

REMARKS

Preparation of mortar and moulding of specimens in accordance with AS 2350.12.

Sampling not carried out by laboratory. Samples tested as received.

This cement is a Type GP cement with up to 7.5% mineral addition.

* NATA accreditation does not cover the performance of this service.

Jul.

Marc Smith
Technical Services Manager
Date of Issue: 6/01/2023