FINAL REPORT

CERTIFICATE No.: 25108



Boral Cement Limited N 62 008 528 523 Taylor Avenue New Berrima NSW 2577 Locked Bag 4 New Berrima NSW 2577 T +61 2 4860 2222

TEST CERTIFICATE OF: Maldon Daily Despatch Off White Cement

PRODUCED AT: Boral Cement Limited Maldon
TESTED AT: Berrima Works Laboratory

SAMPLE IDENTIFICATION: MDDOW2302788
DATE DESPATCHED: 27/07/2023

PROPERTY		REQUIREMENTS OF AS 3972			RESULT
Compressive Strength (AS 2350.11)				
3 Day					43.1 MPa
7 Day		Minimum	35 MPa		53.8 MPa
28 Day		Minimum	45 MPa		64.0 MPa
Setting Time (AS 2350.	4)				
Initial	•	Minimum	45 mins		120 mins
Final		Maximum	360 mins		180 mins
Soundness (AS 2350.5)	Maximum	5 mm		0 mm
SO ₃ (AS 2350.2)		Maximum	3.5 %		2.6 %
CI (AS 2350.2)		Maximum	0.10 %		0.02 %
OTHER REPORTABLE	PROPERTIES				
CHEMICAL			PHYSICAL		
K ₂ O (AS 2350.2)	0.42 %		Normal Consistenc	y (AS 2350.3)	28.5 %
Na ₂ O (AS 2350.2)	0.08 %		Fineness Index	(AS 2350.8)	$400 \text{ m}^2/\text{kg}$
LOI (AS 2350.2)	4.0 %		Brightness *	(TM 10.01.12)	72.0 %

REMARKS

Preparation of mortar and moulding of specimens in accordance with AS 2350.12.

Sampling not carried out by laboratory. Samples tested as received.

This cement is a Type GP cement with up to 7.5% mineral addition.

* NATA accreditation does not cover the performance of this service.

Jul.