FINAL REPORT

CERTIFICATE No.: 25184



N 62 008 528 523 Taylor Avenue New Berrima NSW 2577 Locked Bag 4 New Berrima NSW 2577 T +61 2 4860 2222

TEST CERTIFICATE OF:	Maldon Daily Despatch Off White Cement		
PRODUCED AT:	Boral Cement Limited Maldon		
TESTED AT:	Berrima Works Laboratory		
SAMPLE IDENTIFICATION:	MDDOW2303206		
DATE DESPATCHED:	14/08/2023		

PROPERTY	REQUIREM	ENTS OF AS 3972	RESULT
Compressive Strength (AS 2350.11)			
3 Day			45.5 MPa
7 Day	Minimum	35 MPa	54.7 MPa
28 Day	Minimum	45 MPa	68.5 MPa
Setting Time (AS 2350.4)			
Initial	Minimum	45 mins	135 mins
Final	Maximum	360 mins	180 mins
Soundness (AS 2350.5)	Maximum	5 mm	1 mm
SO ₃ (AS 2350.2)	Maximum	3.5 %	2.8 %
CI (AS 2350.2)	Maximum	0.10 %	0.02 %

OTHER REPORTABLE PROPERTIES								
CHEMIC	AL		PHYSICAL					
K ₂ O (A	AS 2350.2)	0.31 %	Normal Consistency	(AS 2350.3)	28.5 %			
Na ₂ O (A	AS 2350.2)	0.13 %	Fineness Index	(AS 2350.8)	405 m²/kg			
LOI (A	AS 2350.2)	3.9 %	Brightness *	(TM 10.01.12)	72.0 %			


REMARKS

Preparation of mortar and moulding of specimens in accordance with AS 2350.12.

Sampling not carried out by laboratory. Samples tested as received.

This cement is a Type GP cement with up to 7.5% mineral addition.

* NATA accreditation does not cover the performance of this service.



Marc Smith Technical Services Manager Date of Issue: 11/10/2023

Page 1 of 1