## **FINAL REPORT**

CERTIFICATE No.: 25247



Boral Cement Limited N 62 008 528 523 Taylor Avenue New Berrima NSW 2577 Locked Bag 4 New Berrima NSW 2577 T +61 2 4860 2222

TEST CERTIFICATE OF: Maldon Daily Despatch Off White Cement

PRODUCED AT: Boral Cement Limited Maldon
TESTED AT: Berrima Works Laboratory

**SAMPLE IDENTIFICATION:** MDDOW2303511

**DATE DESPATCHED:** 4/09/2023

| PROPERTY                      |             | REQUIREMENTS OF AS 3972 |      |                    |               | RESULT                 |
|-------------------------------|-------------|-------------------------|------|--------------------|---------------|------------------------|
| Compressive Strength (A       | AS 2350.11) |                         |      |                    |               |                        |
| 3 Day                         | •           |                         |      |                    |               | 43.5 MPa               |
| 7 Day                         |             | Minimum                 | 35   | MPa                |               | 53.8 MPa               |
| 28 Day                        |             | Minimum                 | 45   | MPa                |               | 66.9 MPa               |
| Setting Time (AS 2350.        | 4)          |                         |      |                    |               |                        |
| Initial                       | •           | Minimum                 | 45   | mins               |               | 120 mins               |
| Final                         |             | Maximum                 | 360  | mins               |               | 165 mins               |
| Soundness (AS 2350.5          | )           | Maximum                 | 5    | mm                 |               | 0 mm                   |
| SO <sub>3</sub> (AS 2350.2)   |             | Maximum                 | 3.5  | %                  |               | 2.9 %                  |
| CI (AS 2350.2)                |             | Maximum                 | 0.10 | %                  |               | 0.01 %                 |
| OTHER REPORTABLE              | PROPERTIES  |                         |      |                    |               |                        |
| CHEMICAL                      |             |                         |      | PHYSICAL           |               |                        |
| K <sub>2</sub> O (AS 2350.2)  | 0.35 %      |                         |      | Normal Consistency | (AS 2350.3)   | 28.3 %                 |
| Na <sub>2</sub> O (AS 2350.2) | 0.13 %      |                         |      | Fineness Index     | (AS 2350.8)   | 405 m <sup>2</sup> /kg |
| LOI (AS 2350.2)               | 4.1 %       |                         |      | Brightness *       | (TM 10.01.12) | 72.8 %                 |

## **REMARKS**

Preparation of mortar and moulding of specimens in accordance with AS 2350.12.

Sampling not carried out by laboratory. Samples tested as received.

This cement is a Type GP cement with up to 7.5% mineral addition.

\* NATA accreditation does not cover the performance of this service.

Jul.

Marc Smith
Technical Services Manager
Date of Issue: 3/11/2023