## **FINAL REPORT**

CERTIFICATE No.: 25652



Boral Cement Limited N 62 008 528 523 Taylor Avenue New Berrima NSW 2577 Locked Bag 4 New Berrima NSW 2577 T +61 2 4860 2222

TEST CERTIFICATE OF: Maldon Daily Despatch Shrinkage Limited Cement

PRODUCED AT: Boral Cement Limited Maldon

**TESTED AT:** Berrima Works Laboratory

SAMPLE IDENTIFICATION: MDDSL2400159
DATE DESPATCHED: 17/01/2024

| PROPERTY                      |             | REQUIREMENTS OF AS 3972 |                    |               | RESULT                            |
|-------------------------------|-------------|-------------------------|--------------------|---------------|-----------------------------------|
| Compressive Strength (        | AS 2350.11) |                         |                    |               |                                   |
| 3 Day                         | ,           |                         |                    |               | 34.8 MPa                          |
| 7 Day                         |             | Minimum                 | 35 MPa             |               | 48.0 MPa                          |
| 28 Day                        |             | Minimum                 | 45 MPa             |               | 59.3 MPa                          |
| Setting Time (AS 2350.        | 4)          |                         |                    |               |                                   |
| Initial                       |             | Minimum                 | 45 mins            |               | 150 mins                          |
| Final                         |             | Maximum                 | 600 mins           |               | 210 mins                          |
| Soundness (AS 2350.5)         |             | Maximum                 | 5 mm               |               | 1 mm                              |
| SO <sub>3</sub> (AS 2350.2)   |             | Maximum                 | 3.5 %              |               | 2.5 %                             |
| CI (AS 2350.2)                |             | Maximum                 | 0.10 %             |               | 0.02 %                            |
| Shrinkage (AS 2350.13         | )           |                         |                    |               |                                   |
| 28 Day Mean                   |             | Maximum                 | 750 μstrain        |               | 630 µstrair                       |
| OTHER REPORTABLE              | PROPERTIES  |                         |                    |               |                                   |
| CHEMICAL                      |             |                         | PHYSICAL           |               |                                   |
| K <sub>2</sub> O (AS 2350.2)  | 0.57 %      |                         | Normal Consistence | y (AS 2350.3) | 28.3 %                            |
| Na <sub>2</sub> O (AS 2350.2) | 0.07 %      |                         | Fineness Index     | (AS 2350.8)   | $380 \text{ m}^2/\text{kg}$       |
| LOI (AS 2350.2)               | 3.9 %       |                         |                    | ,             | · · · · · · · · · · · · · · · · · |

## **REMARKS**

Preparation of mortar and moulding of specimens in accordance with AS 2350.12.

Sampling not carried out by laboratory. Samples tested as received.

This cement is a Type SL (GP) cement with up to 7.5% limestone mineral addition.

Jul

Marc Smith
Technical Services Manager
Date of Issue: 4/03/2024

Accredited for compliance with ISO/IEC 17025 - Testing

NATA Accreditation Number: 530 / 531

Page 1 of 1