

FINAL REPORT

CERTIFICATE No.: 22727



Boral Cement Limited
ABN 62 008 528 523
Taylor Avenue New Berrima NSW 2577
Locked Bag 4 New Berrima NSW 2577
T +61 2 4860 2222
F +61 2 4860 2257

TEST CERTIFICATE OF: Somerton Daily Despatch Pozzoment
PRODUCED AT: Boral Cement Limited Somerton
TESTED AT: Berrima Works Laboratory
SAMPLE IDENTIFICATION: SDDPZ2102365
DATE DESPATCHED: 21/07/2021

PROPERTY	REQUIREMENTS OF AS 3972		RESULT
Compressive Strength (AS 2350.11)			
3 Day			24.6 MPa
7 Day	Minimum	20 MPa	32.8 MPa
28 Day	Minimum	35 MPa	49.1 MPa
Setting Time (AS 2350.4)			
Initial	Minimum	45 mins	180 mins
Final	Maximum	600 mins	270 mins
Soundness (AS 2350.5)	Maximum	5 mm	1 mm
SO ₃ (AS 2350.2)	Maximum	3.5 %	1.8 %
CI (AS 2350.2)	Maximum	0.10 %	0.02 %

OTHER REPORTABLE PROPERTIES

CHEMICAL

PHYSICAL

Normal Consistency (AS 2350.3)	28.8 %
Fineness Index (AS 2350.8)	380 m ² /kg

REMARKS

Preparation of mortar and moulding of specimens in accordance with AS 2350.12.
Sampling not carried out by laboratory. Samples tested as received.
This blended cement is a Type GB cement with nominally 75% cement / 25% fly ash.



Accredited for compliance with ISO/IEC 17025 - Testing

Marc Smith
Technical Services Manager
Date of Issue: 28/10/2021