

**FINAL REPORT**

**CERTIFICATE No.:** 23875



Boral Cement Limited  
N 62 008 528 523  
Taylor Avenue New Berrima NSW 2577  
Locked Bag 4 New Berrima NSW 2577  
T +61 2 4860 2222

**TEST CERTIFICATE OF:** Somerton Daily Despatch Pozzoment  
**PRODUCED AT:** Boral Cement Limited Somerton  
**TESTED AT:** Berrima Works Laboratory  
**SAMPLE IDENTIFICATION:** SDDPZ2202309  
**DATE DESPATCHED:** 3/06/2022

PROPERTY	REQUIREMENTS OF AS 3972		RESULT
Compressive Strength (AS 2350.11)			
3 Day			25.3 MPa
7 Day	Minimum	20 MPa	35.3 MPa
28 Day	Minimum	35 MPa	52.7 MPa
Setting Time (AS 2350.4)			
Initial	Minimum	45 mins	180 mins
Final	Maximum	600 mins	225 mins
Soundness (AS 2350.5)	Maximum	5 mm	1 mm
SO <sub>3</sub> (AS 2350.2)	Maximum	3.5 %	2.0 %
CI (AS 2350.2)	Maximum	0.10 %	0.01 %

**OTHER REPORTABLE PROPERTIES**

CHEMICAL	PHYSICAL		
	Normal Consistency	(AS 2350.3)	27.7 %
	Fineness Index	(AS 2350.8)	380 m <sup>2</sup> /kg

**REMARKS**

Preparation of mortar and moulding of specimens in accordance with AS 2350.12.  
Sampling not carried out by laboratory. Samples tested as received.  
This blended cement is a Type GB cement with nominally 75% cement / 25% fly ash.



Accredited for compliance with ISO/IEC 17025 - Testing

Marc Smith  
Technical Services Manager  
Date of Issue: 2/09/2022