

FINAL REPORT

CERTIFICATE No.: 21922



Boral Cement Limited
ABN 62 008 528 523
Taylor Avenue New Berrima NSW 2577
Locked Bag 4 New Berrima NSW 2577
T +61 2 4860 2222
F +61 2 4860 2257

TEST CERTIFICATE OF: Waurm Ponds High Early Strength Cement
PRODUCED AT: Boral Cement Limited Waurm Ponds
TESTED AT: Berrima Works Laboratory
SAMPLE IDENTIFICATION: WWDHE2003391
DATE DESPATCHED: 10/11/2020

PROPERTY	REQUIREMENTS OF AS 3972		RESULT
Compressive Strength (AS 2350.11)			
3 Day	Minimum	25 MPa	41.2 MPa
7 Day	Minimum	40 MPa	54.1 MPa
28 Day			67.3 MPa
Setting Time (AS 2350.4)			
Initial	Minimum	45 mins	105 mins
Final	Maximum	360 mins	150 mins
Soundness (AS 2350.5)	Maximum	5 mm	1 mm
SO ₃ (AS 2350.2)	Maximum	3.5 %	2.6 %
Cl (AS 2350.2)	Maximum	0.10 %	0.04 %

OTHER REPORTABLE PROPERTIES

CHEMICAL

K₂O (AS 2350.2) 0.40 %
Na₂O (AS 2350.2) 0.23 %
LOI (AS 2350.2) 1.4 %

PHYSICAL

Normal Consistency (AS 2350.3) 29.5 %
Fineness Index (AS 2350.8) 410 m²/kg

REMARKS

Preparation of mortar and moulding of specimens in accordance with AS 2350.12.
Sampling not carried out by laboratory. Samples tested as received.
This cement is a Type HE (GP) cement with up to 7.5% mineral addition.



Accredited for compliance with ISO/IEC 17025 - Testing


Marc Smith
Technical Services Manager