

Crakfilla

PRODUCT DATA SHEET

Boral Cements Blue Circle® Crakfilla is an economical fine plaster surface filler for wall and ceilings that is grit free and provides a good tradesman like finish.

FEATURES AND BENEFITS

- Easy to use, just add clean water.
- Grit free.
- Excellent finishability.

TYPICAL APPLICATIONS

Filling both horizontal and vertical cracks in plasterboard sheeting.

PREPARATION

Joints or areas to be filled should be dust free and may be required to be dampened to provide better adhesion.

Dust mask and goggles should be used when sanding surfaces.

MIXING

Crakfilla powder should be added to clean potable water.

Always add **Crakfilla** to water, and not the other way around. A workable mix can be achieved by using a ratio of 1kg of powder to 550ml of water in a suitable mixing vessel. Mix to a creamy consistency.

Crakfilla has an initial setting time of 20-30 minutes. Fresh batches of **Crakfilla** should be kept free from previous batch otherwise working life may be shortened.

DO NOT ADD WATER after mix begins to thicken or harden.

AVAILABILITY

Crakfilla comes in 1 and 4kg plastic bags.

CLEANUP & STORAGE

Thoroughly clean all tools and equipment with water promptly after each mix.

Unopened bags can be stored for up to 12 months in a cool dry, weatherproof environment elevated off the floor. Promptly seal any unused material.



SAFE HANDLING

Plasterboard finishing compounds are powders which may contain particles greater than 7 microns, and therefore outside the respirable range unless milled or mechanically crushed. However, inhalation of the dust may aggravate pre-existing respiratory conditions such as asthma and bronchitis.

DO NOT attempt to make an enclosed cast of any body parts such as hands and fingers. This product gives off heat when mixed with water for setting, which may result in serious skin burns after prolonged exposure to body parts.

The use of goggles, dust mask, barrier cream and rubber gloves is recommended.

For further safety information consult the **Material Safety Data Sheet** for the product.

The information in this Data Sheet and any advice given should be viewed as a guide only. Boral makes no guarantee of the accuracy or completeness of the information and recommends you conduct your own testing to determine suitability for your specific purpose.

Revised: July 2012

Boral Cement
ABN: 62 008 528 523

NSW
Clunies Ross Street,
Prospect
NSW 2148
P.O. Box 42 Wentworthville,
NSW 2145
Telephone: (02) 9033 4000
Facsimile: (02) 9033 4055

Victoria
Telephone: 1800 673 570

Tasmania
Telephone: 1800 800 953

Product Support
Telephone: 1800 721 258

