

FINAL REPORT

CERTIFICATE No.: 24393



Boral Cement Limited
N 62 008 528 523
Taylor Avenue New Berrima NSW 2577
Locked Bag 4 New Berrima NSW 2577
T +61 2 4860 2222

TEST CERTIFICATE OF: Tarong Daily Despatch Grade 1 Fly Ash
PRODUCED AT: Boral Cement Limited Tarong
TESTED AT: Berrima Works Laboratory
SAMPLE IDENTIFICATION: TDDFA2204511
DATE DESPATCHED: 29/11/2022

PROPERTY	REQUIREMENTS OF AS 3582.1 - Grade 1	RESULT
Fineness (AS 3583.3)	\geq 75 %	89 %
LOI (AS 3583.3)	\leq 4.0 %	1.9 %
Moisture (AS 3583.2)	\leq 0.5 %	0.2 %
SO ₃ (AS 2350.2)	\leq 3.0 %	0.1 %
SiO ₂ (AS 2350.2)		67.8 %
Al ₂ O ₃ (AS 2350.2)		25.8 %
Fe ₂ O ₃ (AS 2350.2)		1.8 %
Chemical Composition (AS 2350.2)	\geq 70 %	95 %
Total Alkali (AS 2350.2)		0.4 %
Cl (AS 2350.2)	\leq 0.1 %	< 0.01 %

REMARKS

Sampling not carried out by laboratory. Samples tested as received.



Accredited for compliance with ISO/IEC 17025 - Testing

Marc Smith
Technical Services Manager

**Boral Construction Materials
Materials Technical Services**Unit 4, 3-5 Gibbon Road
Baulkham Hills NSW 2153 Australia

PO Box 400, Winston Hills NSW 2153

T +61 (02) 9624 9900

boral.com.au**TEST REPORT – FLYASH****CLIENT:** BORAL CEMENT – (TECHNICAL)**FILE NO:** 50/22**ADDRESS:** 39 Delhi Road, North Ryde, NSW 2113**REQUEST NO:** 103585**SAMPLE IDENTIFICATION:** TDDFA2204511**LAB SAMPLE NO:** 277696**SOURCE OF SAMPLE:** Boral Cement - Berrima**DATE SAMPLED:** 29/11/2022**DATE RECEIVED:** 21/12/2022**IDENTIFICATION OF CEMENT USED:** Boral Cement SL Berrima Ref. 2019**TEST METHOD:** AS 3583: Methods of test for supplementary cementitious materials for use with Portland cement

PROPERTY	DATE TESTED	RESULT	TEST METHOD
Relative density	04/01/2023	2.17	AS 3583.5
Relative water requirement	05/01/2023	100%	AS 3583.6
Relative strength 7 days (accelerated)	05/01/2023	102%	AS 3583.6

Note:

- Sample supplied by the client and tested as received.

Marc Smith, Parisa Sowti, Violeta Paicu, Stephanie Koehler, Mat. File, File

Approved Signatory

Muans Abdulnebe

Date

24.01.2023

Serial No.

CEM103585.MA.1

