

FINAL REPORT

CERTIFICATE No.: 24666



Boral Cement Limited
N 62 008 528 523
Taylor Avenue New Berrima NSW 2577
Locked Bag 4 New Berrima NSW 2577
T +61 2 4860 2222

TEST CERTIFICATE OF: Tarong Daily Despatch Grade 1 Fly Ash
PRODUCED AT: Boral Cement Limited Tarong
TESTED AT: Berrima Works Laboratory
SAMPLE IDENTIFICATION: TDDFA2300894
DATE DESPATCHED: 9/03/2023

PROPERTY	REQUIREMENTS OF AS 3582.1 - Grade 1	RESULT
Fineness (AS 3583.3)	≥ 75 %	82 %
LOI (AS 3583.3)	≤ 4.0 %	2.6 %
Moisture (AS 3583.2)	≤ 0.5 %	< 0.1 %
SO ₃ (AS 2350.2)	≤ 3.0 %	< 0.1 %
SiO ₂ (AS 2350.2)		73.1 %
Al ₂ O ₃ (AS 2350.2)		21.0 %
Fe ₂ O ₃ (AS 2350.2)		1.5 %
Chemical Composition (AS 2350.2)	≥ 70 %	96 %
Total Alkali (AS 2350.2)		0.5 %
Cl (AS 2350.2)	≤ 0.1 %	< 0.01 %

REMARKS

Sampling not carried out by laboratory. Samples tested as received.



Accredited for compliance with ISO/IEC 17025 - Testing

Marc Smith
Technical Services Manager

**Boral Construction Materials
Materials Technical Services**Unit 4, 3-5 Gibbon Road
Baulkham Hills NSW 2153 Australia

PO Box 400, Winston Hills NSW 2153

T +61 (02) 9624 9900

boral.com.au**TEST REPORT – FLYASH****CLIENT:** BORAL CEMENT – (TECHNICAL)**FILE NO:** 50/23**ADDRESS:** 39 Delhi Road, North Ryde, NSW 2113**REQUEST NO:** 104909**SAMPLE IDENTIFICATION:** TDDFA2300894**LAB SAMPLE NO:** 281186**SOURCE OF SAMPLE:** Boral Cement - Berrima**DATE SAMPLED:** 09/03/2023**DATE RECEIVED:** 23/03/2023**IDENTIFICATION OF CEMENT USED:** Boral Cement SL Berrima Ref. 2022**TEST METHOD:** AS 3583: Methods of test for supplementary cementitious materials for use with Portland cement

PROPERTY	DATE TESTED	RESULT	TEST METHOD
Relative density	05/04/2023	2.10	AS 3583.5
Relative water requirement	06/04/2023	102%	AS 3583.6
Relative strength 7 days (accelerated)	13/04/2023	96%	AS 3583.6

Note:

- Sample supplied by the client and tested as received.

Marc Smith, Parisa Sowti, Violeta Paicu, Stephanie Koehler, Mat. File, File

Approved Signatory



Julius Alvaro

Date

19/04/2023

Serial No.

CEM104909.JA.2

Accredited for compliance with ISO/IEC 17025 – Testing
This report shall not be reproduced in full without the approval of the Boral MTS Laboratory.
Test results in this Test Report relate only to the samples tested.

**NATA Accredited Laboratory**
Number: 547