

FINAL REPORT

CERTIFICATE No.: 25499



Boral Cement Limited

N 62 008 528 523

Taylor Avenue New Berrima NSW 2577

Locked Bag 4 New Berrima NSW 2577

T +61 2 4860 2222

TEST CERTIFICATE OF: Tarong Daily Despatch Grade 1 Fly Ash
PRODUCED AT: Boral Cement Limited Tarong
TESTED AT: Berrima Works Laboratory
SAMPLE IDENTIFICATION: TDDFA2305134
DATE DESPATCHED: 22/11/2023

PROPERTY	REQUIREMENTS OF AS 3582.1 - Grade 1	RESULT
Fineness (AS 3583.1)	≥ 75 %	90 %
LOI (AS 3583.3)	≤ 4.0 %	1.7 %
Moisture (AS 3583.2)	≤ 0.5 %	< 0.1 %
SO ₃ (AS 2350.2)	≤ 3.0 %	0.2 %
SiO ₂ (AS 2350.2)		74.1 %
Al ₂ O ₃ (AS 2350.2)		21.0 %
Fe ₂ O ₃ (AS 2350.2)		1.0 %
Chemical Composition (AS 2350.2)	≥ 70 %	96 %
Total Alkali (AS 2350.2)		0.4 %
Cl (AS 2350.2)	≤ 0.1 %	< 0.01 %

REMARKS

Sampling not carried out by laboratory. Samples tested as received.



Accredited for compliance with ISO/IEC 17025 - Testing

Marc Smith
Technical Services Manager

**Boral Construction Materials
Materials Technical Services**Unit 4, 3-5 Gibbon Road
Baulkham Hills NSW 2153 Australia

PO Box 400, Winston Hills NSW 2153

T +61 (02) 9624 9900

boral.com.au**TEST REPORT – FLYASH****CLIENT:** BORAL CEMENT – (TECHNICAL)**FILE NO:** 50/23**ADDRESS:** 39 Delhi Road, North Ryde, NSW 2113**REQUEST NO:** 109440**SAMPLE IDENTIFICATION:** TDDFA2305134**LAB SAMPLE NO:** 295274**SOURCE OF SAMPLE:** Boral Cement - Berrima**DATE SAMPLED:** 22/11/2023**DATE RECEIVED:** 05/12/2023**IDENTIFICATION OF CEMENT USED:** Boral Cement SL Berrima Ref. 2022**TEST METHOD:** AS 3583: Methods of test for supplementary cementitious materials for use with Portland cement

PROPERTY	DATE TESTED	RESULT	TEST METHOD
Relative density	12/12/2023	2.11	AS 3583.5
Relative water requirement	14/12/2023	101%	AS 3583.6
Relative strength 7 days (accelerated)	21/12/2023	98%	AS 3583.6

Note:

- Sample supplied by the client and tested as received.

Marc Smith, Parisa Sowti, Violeta Paicu, Mat. File, File

Approved Signatory



Sam El-Hamawi

Date

22/12/23

Serial No.

CEM109440.SE.1

Accredited for compliance with ISO/IEC 17025 – Testing

This report shall not be reproduced in full without the approval of the Boral MTS Laboratory.

Test results in this Test Report relate only to the samples tested.

**NATA Accredited Laboratory**
Number: 547